

Sierra White

Specifying the stone

Quarry details

Finike, Southern Turkey

Supplier

Realstone Limited

Wingerworth

Derbyshire S42 6RG

Contact

sales@realstone.co.uk

Masonry sales

Realstone Head Office UK
Wingerworth, Chesterfield
Derbyshire S42 6RG
England UK

tel +44 (0)1246 270244
fax +44 (0)1246 220095
email sales@realstone.co.uk

Realstone Scotland UK
Barclay Curle Complex
739 South Street, Whiteinch
Glasgow G14 0AH
Scotland UK

tel +44 (0)141 954 1161
fax +44 (0)141 954 1261
email glasgow@realstone.co.uk

Realstone Cumbria UK
Stonerise Quarry Lazonby
Cumbria CA11 9NF
England UK

tel +44 (0)1768 865811
fax +44 (0)1768 890874
email lazonby@realstone.co.uk



limestone

Technical results

Description	A fine-grained hard white limestone	
Country of origin	Turkey	
Geological type	Limestone	
Colour	Plain white	
Density	2210 kg/m ³	BS EN 1936 (1999)
Absorption	6.1 %	BS EN 13755 (2002)
Compressive strength	41 MPa	BS EN 1926 (1999)
Porosity	18.10 %	BS EN 1936 (1999)
Flexural strength	6.42 MPa	BS EN 13161 (2001)
Average block size	1700mm x 1700mm x 1500 mm	

Please note that stone is a natural product and all results are subject to variation



Realstone

www.realstone.co.uk