

# Silver Star Black Granite

## Specifying the stone

### Quarry details

Mongolia, P R, China

### Supplier

Realstone Limited  
Wingerworth  
Derbyshire S42 6RG

### Contact

[sales@realstone.co.uk](mailto:sales@realstone.co.uk)

## Masonry sales

**Realstone Head Office UK**  
Wingerworth, Chesterfield  
Derbyshire S42 6RG  
England UK

tel +44 (0)1246 270244  
fax +44 (0)1246 220095  
email [sales@realstone.co.uk](mailto:sales@realstone.co.uk)

**Realstone Scotland UK**  
Barclay Curle Complex  
739 South Street, Whiteinch  
Glasgow G14 0AH  
Scotland UK

tel +44 (0)141 954 1161  
fax +44 (0)141 954 1261  
email [glasgow@realstone.co.uk](mailto:glasgow@realstone.co.uk)

**Realstone Cumbria UK**  
Stonerise Quarry Lazonby  
Cumbria CA11 9NF  
England UK

tel +44 (0)1768 865811  
fax +44 (0)1768 890874  
email [lazonby@realstone.co.uk](mailto:lazonby@realstone.co.uk)



granite

## Technical results

Description	High quality fine-grained black granite with exceptionally good technical characteristics	
Country of origin	China	
Geological type	Granite Basalt	
Colour	Black	
Density	2855 kg/m <sup>3</sup>	BS EN 1936 (1999)
Absorption	0.14 %	BS EN 13766 (2002)
Breaking load at dowel hole	Mean 5663.9 N	BS EN 13364 (2002)
Porosity	0.5 %	BS EN 1936 (1999)
Flexural strength	Dry 37.4 MPa Wet 37.9 MPa	BS EN 13161 (2001)
Saturation co-efficient	0.84	
Acid immersion	Passed	BRE SP8/04/J

Please note that stone is a natural product and all results are subject to variation



**Realstone**

[www.realstone.co.uk](http://www.realstone.co.uk)